

Technical Datasheet

STEP Parquet lacquer 2K Satin #6560



Applications:

Water borne 2-component polyurethane finish. Excellent for heavy duty use with a lot of traffic. To be applied as a finishing coat on pretreated surfaces in concrete, wood, linoleum, cork, etc. Always make a test sample on unknown surfaces. Read our STEP Instructions for Use for comprehensive instructions and legend of used symbols. For specific questions, do not hesitate to call or app at 0031 6 47057824.

The figures in the scheme below are valid for the mixed product. Circumstances for drying are standardized at 20°C, 65% RAH and sufficient ventilation.

Colour	Pale white liquid, dries transparent and clear. Doesn't yellow.
Degree of gloss	Satin
Odour	Mild
Solids	≈ 34 VOL %
pH	7.5
Viscosity/fluidity	Thin liquid
Sanding	Good
Yield	8 - 12 m ² per litre
Dust dry	1 hour
Next coat	3 - 4 hours
Light first use	12 hours
Fully dutiable	3 days (whilst drying, don't lay carpets, foil, cloth)
Scratch proof	Very resistant to scratching like sand under shoes, etc.
Wear resistance	Very long lasting
Resistance to fluids and chemicals	Good chemical resistance against water, alcohol and detergents, spills of tea, wine, coffee.
Anti-slip,	Suitable for daily traffic, walking
Complies with	AgBB/DiBt (Germany), Indoor Air Quality Decree (Belgium)

Technical Datasheet

STEP Parquet lacquer 2K Satin #6560

Available in:

1 litre bottle; art.nr. 5545233; EAN 8716544037922 (Box 12 x 1 litre)

A-component = 0,94 ltr, B-component = 0,06 ltr

4 litre can; art.nr. 5545239; EAN 8716544037939 (Box = 4 x 4 litre)

A-component = 3,76 ltr, B-component = 0,24 ltr

See SAFETY DATASHEET for a safe and healthful job.